

VICTORIA S3 SRC



DESCRIERE	NORMA EN ISO 20345:2011	RESULTAT CERINTE NORMA	
Fete: Piele pigmentata, hidrofobizata	5.4.3 Rezistenta la sfasiere 5.4.6 Coeficient de Permeabilitatea la vapori de apa	207 N 1.2 mg/cm ² h 18.8 mg/cm ²	≥120 N ≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
Captuseala caputa : Material textil perforat, rezistenta la abraziune ce asigura respiratia piciorului	5.5.1 Rezistenta la sfasiere 5.5.2 Rezistenta la abraziune (mediu umed) Rezistenta la abraziune (mediu uscat) 5.5.3 Permeabilitatea vaporilor de apa Coeficient de permeabilitate	45 N Fara decupaj Fara decupaj 4.7mg/cm ² h 40.5 mg/cm ² h	≥ 15 N 25.600 cicluri 12.800 cicluri ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
Captuseala stail: Tesatură respirabilă, rezistenta la abraziune	5.5.1 Rezistenta la sfasiere 5.5.2 Rezistenta la abraziune (mediu umed) Rezistenta la abraziune (mediu uscat) 5.5.3 Permeabilitatea vaporilor de apa Coeficient de permeabilitate	38 N Fara decupaj Fara decupaj 7.8 mg/cm ² h 63.3 mg/cm ² h	≥ 15 N 51.200 cicluri 25.600 cicluri ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
Bombeu de siguranta: Nemetalic, din policarbonat	5.3.2.3 Rezistenta la impact 5.3.2.4 Rezistenta la compresiune	14.5 mm 15.5 mm	≥ 14 mm ≥ 14 mm
Lamela antiperforare: Lamela nemetalica	5.7.1 Grosime 5.7.3 Absorbția de apa	3.6 mm 97 mg/cm ²	≥ 2 mm ≥ 70.0mg/cm ²

Acoperis de brant: X-DRY Detasabil,anatomic, antistatic,	5.7.4.2 Rezistenta la abraziune (mediu umed) Rezistenta la abraziune (mediu uscat)	Fara perforatii Fara perforatii	25.600 cicluri 12.800 cicluri
Talpa: PU 2D, antialunecare SRC	5.8.2 Rezistenta la sfasiere 5.8.3 Rezistenta la abraziune 5.8.4 Rezistenta la flexare 5.8.5 Hidroliza 5.10 Antistatic 6.4.2 Rezistenta la uleiuri 5.11 Rezistenta la alunecare pe placi ceramice spalate cu detergent Alunecare pe suprafata totala a talpii Alunecare pe calcai Rezistenta la alunecare pe placi din otel acoperite cu glicerina Alunecare pe suprafata totala a talpii Alunecare pe calcai	9.1 kN/m 63 mm ³ 2.0 mm 2.5m Uscat : 2,39 x108Ω Umed: 7,56 x107Ω 8% 0,44 0,29 0,18 0,13	≥ 8 kN/m ≤150mm ³ ≤ 4,0 mm ≤ 6,0 mm ≤ 12% ≥ 0,32 ≥ 0,28 ≥ 0,18 ≥ 0,13

MARIMI : 35-48

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519 C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207
www.exena.it – info@exena.it - pec: amministrazione@pec.exena.it

VICTORIA S3 SRC



DESCRIPTION	NORM EN ISO 20345:2011	RESULT	REQUIREMENT
UPPER: water resistant pigmented leather	5.4.3 Tear strength	207 N	≥120 N
	5.4.6 Water vapor permeability Coefficient	1,2 mg/cm ² h 18,8 mg/cm ²	≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
VAMP LINING: Breathable, abrasion resistance.	5.5.1 Tear strength	45 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet) Abrasion resistance(Dry)	No fori No fori	25.600 cycles 12.800 cycles
	5.5.3 Water vapor permeability Coefficient	4,7 mg/cm ² h 40,5 mg/cm ²	≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
QUARTER LINING: Breathable, abrasion resistance.	5.5.1 Tear strength	38 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet) Abrasion resistance(Dry)	No fori No fori	51.200 cycles 25.600 cycles
	5.5.3 Water vapor permeability Coefficient	7,8 mg/cm ² h 63,3 mg/cm ²	≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
SAFETY TOE CAP: Non-metallic polycarbonate safety toe.	5.3.2.3 Impact resistance	14,5 mm	≥ 14 mm
	5.3.2.4 Compression resistance	15,5 mm	≥ 14 mm
PIERCE-RESISTANCE: Textile pierce proof footbed,	5.7.1. Thickness	3,6 mm	≥ 2,0 mm
	5.7.3 Water absorption	97 mg/cm ²	≥70,0 mg/cm ²
FOOTBED: X-DRY Removable, cushioned, antistatic insole.	5.7.4.2 Abrasion resistance(Wet)	No holes	25.600 cycles
	Abrasion resistance(Dry)	No holes	12.800 cycles
OUTSOLE: PU 2D, Antislip SRC	5.8.2 Tear strength	9,1 kN/m	≥ 8 kN/m
	5.8.3 Abrasion resistance	63 mm ³	≤ 150 mm ³
	5.8.4 Flexing resistance	2 mm	≤ 4,0 mm
	5.8.5 Hydrolysis	2,5 mm	≤ 6,0 mm
	5.10 Antistatic	secco: 2,39 x10 ⁸ Ω umido: 7,56 x10 ⁷ Ω	
	6.4.2 Oils resistance	8.0 %	≤ 12%
	5.11 Pressed ceramic tile floor on detergent resistance		
	Flat slip	0,44	≥ 0,32
	Heel slip	0,29	≥ 0,28
	Stainless steel plate on glycerin resistance		
Flat slip	0,18	≥ 0,18	
Heel slip	0,13	≥ 0,13	

SIZES: 35-48

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207

www.exena.it – info@exena.it - pec: amministrazione@pec.exena.it

Traducere din limba engleza - in conformitate cu documentul

EXENA
DECLARATIE DE CONFORMITATE UE
M22 -Vers. 00

Conform regulamentului (UE) 2016/425 – Anexa IX, **Exena srl** DECLARA ca echipamentul individual de protectie si lotul respectiv de productie descris mai jos:

Articol: **VICTORIA**

Lot: 69001



Este in conformitate cu standardul: EN ISO 20345:2011

Clasa: II

Categoria de marcaj: S3 SRC

Nr. certificat: F-130-04460-21

Data: 12.05.2021

EMIS DE: CIMAC – 0465

Civitanova Marche,

Aplicata parafa firmei EXENA S.R.L.

Sediul in Via Breda, 7/A

Civitanova Marche (MC), ITALIA ,

Sfârșitul traducerii

DECLARATION OF CONFORMITY UE

M22 - Ver.00

As per Regulation (UE) 2016/425 - Annex IX, Exena Srl declares that the ppe and the relative production batch below described:

item

VICTORIA

batch:

69001



conforms to the standard:

EN ISO 20345:2011

class:

II

marking category:

S3 SRC

certificate numb.:

F-130-04460-21

date:

12/05/2021

issued by:

CIMAC - 0465

Civitanova Marche

~~EXENA S.r.l.
Via Breda, 7/A - Zona Ind. A
Tel. 0733 897256 Fax 0733 897814
P. IVA: 01336080435 - MC
R. IVA: 01336080435 - MC
CEO~~

EXENA S.r.l.

Via Breda, 7 – Z.na Ind. A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

P. IVA: 01336080435 - Reg. Impr. Trib. MC N. 21676/1998 - CCIAA MC 22988

www.exena.it – info@exena.it – pec: amministrazione@pec.exena.it